

<b>ALBROMET 340</b>	<b>Data sheet aluminiumbronze</b>
<b>Material properties:</b>	Very high compressive strength, good sliding properties, high hardness with small elongation, not impact-resistant
<b>Application examples:</b>	Wear partner for hardened steel grades, forming tools for bending, embossing, profiling and thermoforming of stainless steel plates and tubes.
<b>Machining tips:</b>	Machine only with carbide-equipped tools Recommendation: <i>Hoffmann GmbH, München</i> <i>Tel. 089-8391-0, Fax: 089-8391-89</i> <i>www.hoffmann-group.com</i> Welding is restricted possible.
<b>Typical analysis:</b>	Al 14,0 % Fe 5,0 % Others 2,0 % Cu Balance
<b>Standards/Specifications:</b>	Not standardized
<b>Delivery formats:</b>	Forged parts, Castings, Extruded rods, Semi-finished products, Finished parts based on drawings
<b>Mechanical and physical properties:</b>	
Brinell hardness (HB 30) Tensile strength Rm Yield strength Rp 0,2 Elongation at break A5 Density Compressive strength Elasticity modulus E Mean linear coefficient of thermal expansion Thermal conductivity at 20°C Electrical conductivity  Temperature resistance  Permeability	320 - 360 > 630 N/mm <sup>2</sup> > 540 N/mm <sup>2</sup> 0,5 % 7,1 g/cm <sup>3</sup> 1300 Mpa 105,0 KN/mm <sup>2</sup> 17,5 10 <sup>-6</sup> /K 40 W/m x k 4,06 m/Ohm x mm <sup>2</sup>  < 300°C up to the clear change in strength value  1,12 H = 100 Oe

This data is based on information provided by our supplying plants. All changes reserved. The mechanical strength values are typical standard values and depend on the measurement and the production method.

Version 02/2012